

Physical property	Typical value	Test method
Appearance	Gray	
Solids Content by Volume	100%	ASTM D1644-2001, Method A
Elongation	88%	D412-06ae2 (as per C957M-10)
Hardness	58 Shore D	D2240-05 (as per C836M-10)
Tear Resistance	230 pli	D624-00 (2007)
Tensile Strength	1873 psi	D412-06ae2 (as per C957M-10)
VOC Content (maximum)	0 g/l	ASTM C1250-05

### Description

**Henry® GP Wearcoat** is a 100% solids, two-component, polyurethane coating, fully broadcast with aggregate, to form a flexible, hard wearing, anti-skid, traffic surface.

**GP Wearcoat** also forms a surface for strong adhesion by mortars, concrete, asphalt, adhesives and sealants.

### Features

- Flexible, hard wearing, anti-skid traffic surface
- Cures quickly at low temperatures
- Low odor, solvent free and VOC compliant

### Usage

**GP Wearcoat** is used as a hard-wearing traffic surface for:

- Parking Decks, Loading Docks, Balconies, Walkways
- Protected Membrane Roofing (PMR)
- Plaza Decks
- Inverted Roof Membrane Assemblies (IRMA)
- Green Roofs (VRA)
- Split Slabs
- Planters
- Terraces

### Application

**Site Conditions:** All surfaces should be prepared per the approved Henry specification and TechTalk.

Surface temperature must be at least 5° F (-15° C) above the dew point and rising.

Air and substrate temperatures must be between 40° F (5° C) and 95° F (35° C). Relative humidity must be less than 80%.

**Surface Prep:** Surfaces to be over-coated must be clean, dry and free of contaminants that would impair adhesion.

If there are any doubts about suitability of a substrate, further advice should be sought from a Henry representative and a small trial area should be applied and tested appropriately.

**Product Mixing:** **GP Wearcoat** Parts A & B are pre-measured.

Mix all Part A with all of Part B.

They must be thoroughly mixed, using an electric, slow speed (300-400rpm), high torque drill with spiral (Jiffy) mixing paddle.

#### Mix Ratio by Volume:

1. Dispense Part A into a separate, clean, dry mixing pail. Mix for 30 seconds, taking care not to hit the sides.
2. Add Part B, taking care not to hit the sides, and mix for a minimum 1 minute.

Work the mixing paddle around the sides and bottom of the mixing pail to achieve a uniform, streak free, homogenous liquid. Scrape out all the material from the mixing pail.

## Henry GP Wearcoat

---

Decant to a new pail and use immediately.

Do not mix new material with old, uncured material as this can significantly reduce work times. Use new pails frequently. Decant newly mixed material into smaller containers or onto substrate and spread to prolong working time.

**Pot Life @ 68° F (20° C): 15 minutes.** The working time and viscosity of **GP Wearcoat** will be influenced by the length of time it is mixed (longer mixing results in shorter pot life), the substrate and ambient temperatures and how quickly it is removed from the mixing pail and spread on the substrate.

**Application: GP Wearcoat** is applied evenly by notched (3/16") squeegee and back rolled with a heavy-duty roller arm and medium nap (1/2") (13 mm) roller to assist leveling.

When **GP Wearcoat** becomes less fluid, back roll one more time to ensure it stays on substrate high points.

When **GP Wearcoat** has a sticky, "taffy" like consistency (usually 15-20 minutes @ 68° F / 20° C), broadcast clean, dry aggregate as specified.

Apply aggregate by shovel or hopper gun, in multiple passes, allowing aggregate to "fall" vertically onto the **GP Wearcoat**

### Application Rate:

- Apply in one coat at a rate of 45-65 sf/gal (150-220 st/ 3.35 gal kit), depending on Henry specification
- Allow for saturation of rollers and brushes

**WFT-DFT:** Both 24-35 mils, depending on applicaton rate.

### Re-coat and Traffic Times after application:

Minimum @ 68° F (20° C) = 4 hours

Maximum 24 hours. No maximum time when fully broadcast with sand but must be cleaned thoroughly before over coating

Colder temperatures will increase this time.

### Product Restrictions and Limitations:

Can be rained on after 3 hrs. @68° F (20° C)

Can be walked on after 4 hrs. @68° F (20° C)

Colder temperatures will increase these times

**NOTE:** Before using **GP Wearcoat**, please refer to Safety Data Sheet (SDS). Ensure the same safe working methods are followed for all persons in the work area. Wear suitable protective clothing, butyl rubber or nitrile gloves and safety goggles with side shields during mixing and application.

Respiratory masks should be worn at all times when adequate ventilation does not exist.

A NIOSH/MSHA (TC-23C-1809), multi gas vapor respirator is acceptable.

Avoid strong concentration of vapor as well as direct contact with skin or eyes.

Uncured resins may be toxic. They may cause allergic reactions or hypersensitivity reactions

Contact with skin – wash immediately with soap and water.

Contact with eyes – rinse immediately with lots of water and seek medical attention.

## Coverage

---

Application rates should be adjusted to meet each project's specified requirements. Coverage rates are theoretical and do not take into account material loss due to project conditions and working methods.

- For Henry System Warranty and Gold Seal Warranty requirements, refer to appropriate approved Henry specification for application and coverage rate requirements.

## Clean-up

---

Clean-up of tools and equipment may be accomplished by using Acetone or MEK. Read and follow all Health and Safety instructions on SDS. Wash body with soap and water. Ensure all materials are mixed and cured before disposal, in accordance with federal, state, and local regulations. Dispose of all packaging in accordance with federal, state, and local regulations.

## Henry GP Wearcoat

---

### Product contents / packaging size

---

Part A 2.49 gal / 3.5 gal container  
Part B .95 gal / 1 gal container

### Storage

---

One year in unopened containers stored between 50° F (10° C) and 80° F (27° C) under dry, ventilated conditions, and out of direct sunlight.

Storing the material at a higher temperature may reduce its shelf life. Keep in an upright position and do not over stack.

For more information, visit [www.henry.com](http://www.henry.com) or for technical assistance call us at 800-486-1278. For more information on the Henry® product warranty and liability disclaimer please visit [www.henry.com/warranty](http://www.henry.com/warranty). Refer to the Safety Data Sheet prior to using this product. The Safety Data Sheet is available at [www.henry.com](http://www.henry.com) or by emailing Henry® Product Support at [productsupport@henry.com](mailto:productsupport@henry.com) or by calling 800-486-1278.

Henry is a registered trademark of Henry Company.  
Covered by US patent 6,901,712; Canadian patent 2,413,550.

The technical and application information herein is based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use. Henry® Company data sheets are updated on a regular basis; it is the user's responsibility to obtain and to confirm the most recent version. Information contained in this data sheet may change without notice.