



NOTES:

1. DETAIL SHOWS HENRY **DUNDEQ** SYSTEM PARTIAL SEED AND LOCK TRAFFIC COATING. SUBSTRATE SHOWN IS FOR REFERENCE ONLY. REFER TO PRODUCT SPECIFIC TECHNICAL DATA SHEET FOR AUTHORIZED SUBSTRATES.
2. HENRY **DUNDEQ** SYSTEM STANDARD PRIMERS: **HENRY LV PRIMER** AND **HENRY LVXL PRIMER**.
3. OTHER RECOMMENDED PRIMERS INCLUDE: **HENRY ST PRIMER** AND AGGREGATE, **HENRY STXL PRIMER** AND AGGREGATE, **PUMADEQ PRIMER 20** AND AGGREGATE OR **HENRY GC EPOXY PRIMER**. REFER TO THE **DUNDEQ** SYSTEM SUBSTRATE PRIMER GUIDELINES TECH-TALK BULLETIN FOR APPLICATION RECOMMENDATIONS.
4. PARTIALLY BROADCAST DRY SILICA SAND INTO FIRST LAYER OF WET TOP COAT (SIEVE SIZE: #20-50, #12 SILICA OR NJ0-NJ00).
5. REMOVE EXCESS PRIMER FROM CRACK PRIOR TO APPLYING **HENRY DUNDEQ GP FLEXCOAT**.
6. DO NOT INSTALL **DUNDEQ** SYSTEM BEYOND PRIMED SURFACES.
7. CRACKS GREATER THAN 1/8" WIDE ARE CONSIDERED EXPANSION JOINTS. REFER TO EXPANSION JOINT DETAILS.
8. REFER TO **DUNDEQ** SYSTEM GUIDE SPECIFICATION AND **DUNDEQ** SYSTEM DETAILS FOR RECOMMENDED INSTALLATION PROCEDURES.

Henry[®]

999 N. Pacific Coast Highway, Suite 800
El Segundo, CA 90245
800-486-1278 • www.henry.com

MANUFACTURER GUIDE DETAILS ARE FOR REFERENCE ONLY. HENRY DOES NOT ASSUME RESPONSIBILITY FOR ERRORS OR DEVIATIONS IN DESIGN OR ENGINEERING. PROJECT SPECIFIC VERIFICATION IS RECOMMENDED PRIOR TO INSTALLATION.

DUNDEQ SYSTEM - PEDESTRIAN/VEHICULAR TRAFFIC COATING

NON-MOVING JOINT
PARTIAL SEED AND LOCK TRAFFIC COATING
CRACKS GREATER THAN 1/16" WIDE

SCALE: N.T.S. 04-10-2020

DUNDEQ-SC4